



# CHEMPLAX LLC

A KMI Group Company

Technical Data Sheet

## EcoPrene 51% PCR 65A Black TPV

Thermoplastic Vulcanizate (TPV)

### Product Description

EcoPrene 51% PCR 65A Black TPV is a post-consumer recyclable thermoplastic vulcanizate containing an olefin-based rubber and polyolefin resins. It is designed for applications requiring long term sealing performance even at elevated temperatures. Soft-touch feel for grips and handles used in automotive and consumer goods. It can be processed using conventional thermoplastic processing equipment that can be extruded or molded into flexible parts. It is an excellent choice for applications requiring flexibility.

### Revision

Revision Date: 2/21/24

Properties	Method	Value
Melt Flow Rate @ 230°C	ASTM D1238	3.1 g/10 min
Density	ASTM D792	0.970 g/cm <sup>3</sup>
Durometer Shore A	ASTM D2240	65
Tensile Properties	ASTM D412	
Tensile Strength 100%		2.90 MPa
Tensile Strength		8.00 MPa
Elongation		550%

### Additional Notes

**Processing Parameters:** EcoPrene material can be processed using conventional thermoplastic processing equipment. Extrusion processing recommendation L/D ratio of 24 or more, and a metering type screw with compression ratio of 3-4.

**For additional inquiries, please contact: [csr.supplychain@kmigroup.com](mailto:csr.supplychain@kmigroup.com)**

TECHNICAL INFORMATION AND DATA REGARDING THE COMPOSITION, PROPERTIES OR USE OF THE PRODUCTS DESCRIBED HERE IS BELIEVED RELIABLE. HOWEVER NO REPRESENTATION OR WARRANTY IS MADE WITH RESPECT THERETO EXCEPT AS MADE BY CHEMPLAX LLC IN WRITING AT TIME OF SALE. CHEMPLAX LLC CANNOT ASSUME RESPONSIBILITY FOR ANY PATENT LIABILITY WHICH MAY RISE FROM THE USE OF ANY PRODUCT IN A PROCESS, MANNER OR FORMULA NOT DESIGNED BY CHEMPLAX LLC.