

Technical Data Sheet

Elastoprene 60 NA

Thermoplastic Vulcanizate (TPV)

Product Description

Elastoprene 60 NA is a thermoplastic vulcanizate derived from an olefin-based rubber and polyolefin resins. It is designed for applications requiring long term sealing performance even at elevated temperatures. It can be processed using conventional thermoplastic processing equipment that can be extruded or molded into flexible parts. It combines good physical properties and chemical resistance for use in a wide variety of applications, including high flex fatigue resistance and UV resistance.

Revision		
Revision Date: 4/18/23		
Properties	Method	Value
Melt Flow Rate @ 230°C	ASTM D1238	12.9 g/10 min
Density	ASTM D792	0.885 g/cm ³
Durometer Shore A	ASTM D2240	72
Tensile Properties	ISO 37	
Tensile Strength 100%		2.85 Mpa
Tensile Strength		7.40 Mpa
Elongation		510%

Additional Notes

Processing Parameters: Elastoprene material can be processed using conventional thermoplastic processing equipment. Extrusion processing recommendation L/D ratio of 24 or more, and a metering type screw with compression ratio of 3-4. Die swelling will be limited due to the higher melt viscosity.

For additional inquiries, please contact: csr.supplychain@kmigroup.com

TECHNICAL INFORMATION AND DATA REGARDING THE COMPOSITION, PROPERTIES OR USE OF THE PRODUCTS DESCRIBED HERE IS BELIEVED RELIABLE. HOWEVER NO REPRESENTATION OR WARRANTY IS MADE WITH RESPECT THERETO EXCEPT AS MADE BY CHEMPLAX LLC IN WRITING AT TIME OF SALE. CHEMPLAX LLC CANNOT ASSUME RESPONSIBILITY FOR ANY PATENT LIABILITY WHICH MAY RISE FROM THE USE OF ANY PRODUCT IN A PROCESS, MANNER OR FORMULA NOT DESIGNED BY CHEMPLAX LLC.